

Art Clay World, USA

Melting Points of Selected Metals

3/22/2005
 866-381-0100
www.artclayworld.com

METAL		Degrees °C	Degrees °F
Aluminum	-	660.2	1220.4
Brass	-	954	1749
Nu-Gold	-	1030	1886
Red Brass	-	1044	1910
Bronze	-	1060	1945
Copper	-	1083	1981.4
Gold	22k yellow	1063	1954.5
	18k green	988	1810
	18k yellow	927	1700
	18k white	943	1730
	18k red	902	1655
	14k green	963	1765
	14k yellow	879	1615
	14k white	996	1825
	14k red	935	1715
	10k green	860	1580
	10k yellow	907	1665
	10k white	1079	1975
10k red	960	1760	
Iron	-	1535	2793
Nickel Silver	-	1110	2030
Palladium	-	1554	2829
Platinum	-	1773.5	3224.3
	15% Iridio-Plat.	1821	3310
	10% Iridio-Plat.	1788	3250
	5% Iridio-Plat.	1779	3235
Silver	Fine 99.9%-Silver	960.5	1760.9
	Sterling 92.5%-Silver	893	1640
	Coin	879	1615
Steel	99Fe 1C	1511	2750
Stainless Steel	91Fe 9C	1371	2500
Titanium	-	1800	3272