

Art Clay World, USA

Temperature Conversion To Standard Pyrometric Cones

3/8/2005
866-381-0100
www.artclayworld.com

Cones #	Small Cones		Large Cones		Segger Cones
	300°C	540°F	150°C	270°F	Temp. in °C
020	666	1231	635	1175	670
019	723	1333	683	1261	690
018	752	1386	717	1323	710
017	784	1443	747	1377	730
016	825	1517	792	1458	750
015	843	1549	804	1479	790
014	—	—	838	1540	815
013	—	—	852	1566	835
012	—	—	884	1623	855
011	—	—	894	1641	880
010	919	1686	894	1641	900
09	955	1751	923	1693	920
08	983	1801	955	1751	940
07	1008	1846	984	1803	960
06	1023	1873	999	1830	980
05	1062	1944	1046	1915	1000
04	1098	2008	1060	1940	1020
03	1131	2068	1101	2014	1040
02	1148	2098	1120	2048	1060
01	1178	2152	1137	2079	1080
1	1179	2154	1154	2109	1100
2	1179	2154	1162	2124	1120
3	1196	2185	1168	2134	1140
4	1209	2208	1186	2167	1160
5	1221	2230	1196	2185	1180
6	1255	2291	1222	2232	1200
7	1264	2307	1240	2264	1230
8	1300	2372	1263	2305	1250
9	1317	2403	1280	2336	1280
10	1330	2426	1305	2381	1300
11	1336	2437	1315	2399	1320
12	1355	2471	1326	2419	1350
13	—	—	1346	2455	1380
14	—	—	1366	2491	1410
15	—	—	1431	2608	1430